

**CERTIFICATE OF ANALYSIS**

**CERTIFICATE NO.** 2006-04-008.1D

**CUSTOMER**

**CUSTOMER REF.**

**Sample Ref**

Trespa International BV  
Wetering 20  
NL-6002 SM Weert  
The Netherlands

**SAMPLE DETAILS**

**DATE RECEIVED**

16-May-06

Toplabplus

**METHOD: (Determination of Antibacterial Activity using Test Based on JIS Z 2801: 2000)**

**DATE ANALYSED** 22-May-06

**DATE REPORTED**

25-May-06

**RESULTS (AS CFU CM -2)**

SAMPLE	SPECIES	CONTACT TIME		LOG REDUCTION	% REDUCTION
		0	24		
Toplabplus	<i>Escherichia coli</i>	1.5E+04	< 1	4.2	> 99.99%
Polypropylene	<i>Escherichia coli</i>	1.5E+04	2.6E+05		
Toplabplus	<i>Staph aureus</i>	1.3E+04	< 1	4.1	> 99.99%
Polypropylene	<i>Staph aureus</i>	1.3E+04	9.6E+03		

The above data shows the change in the population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95%.

INDUSTRIAL MICROBIOLOGICAL SERVICE LTD  
PALE LANE  
HARTLEY WINTNEY  
HANTS  
RG27 8DH  
UK

PETER D ASKEW  
MANAGING DIRECTOR

