

# Technical data sheet



## Polystone® Safe-Tec C

### Product characteristics

- High chemical resistance
- Anti-slip properties even in wet surface

### Typical field of application

- Chemical engineering and tank building
- Drinking and waste water technology

	Test method	Unit	Value
<b>General properties</b>			
Density	DIN EN ISO 1183-1	g/cm <sup>3</sup>	0,96
Water absorption	DIN EN ISO 62	%	<0,05
Flammability (Thickness 3 mm / 6 mm)	UL 94		HB
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	N/mm <sup>2</sup>	20
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	800
Notched impact strength (charpy)	DIN EN ISO 179	kJ/m <sup>2</sup>	12
Shore hardness	DIN EN ISO 868	scale D	59
<b>Thermal properties</b>			
Melting temperature	ISO 11357-3	°C	135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> K <sup>-1</sup>	150-230
Service temperature, long term	Average	°C	-30 ... 100
Service temperature, short term (max.)	Average	°C	100
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	67
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		2,5
Dielectric dissipation factor (10 <sup>6</sup> Hz)	IEC 60250		0,0004
Volume resistivity	IEC 60093	Ω *cm	>10 <sup>14</sup>
Surface resistivity	IEC 60093	Ω	>10 <sup>14</sup>
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV/mm	45

The data stated above are average values ascertained by statistical tests on a regular basis. They are in accordance with DIN EN 15860. The data above are provided purely for information and shall not be regarded as binding unless expressly agreed in a contract of sale.