

## **Master Specification for Aluminium Profiles**

**Scope of application:** This specification defines the basic requirements for all extruded aluminium profiles,

purchased by profine

Class of goods: HAWA (traded goods) aluminium-profiles (701535000)

Material: EN AW – 6060 T66 according to DIN 755-2

Place of label: Front side

Label: Product-/article number, SAP number, content of packaging units, profine Logo

Other applicable Standards: DIN EN 755-1:1997-08 - Extruded rod/bar, tube and profiles

Part 1: Technical conditions for inspection and

delivery

DIN EN 755-2:1997-08 - Extruded rod/bar, tube and profiles

Part 2: Mechanical properties

DIN EN 12020-1:2001-07 - Extruded precision profiles in alloys

EN AW-6060 and EN AW-6063

Part 1: Technical conditions for inspection and

delivery

DIN EN 12020-2:2001-07 - Extruded precision profiles in alloys

EN AW-6060 and EN AW-6063

Part 2: Tolerances on dimension and form

DIN EN12206-1:2004-09 - Paints and varnishes - Coating of aluminium and

aluminium alloys for architectural purposes Part 1: Coatings prepared from coating powder

DIN 17611:2011-11 - Anodized products of aluminium and wrought

aluminium alloys - Technical conditions of delivery

**Fastness to weathering:** GSB AL 631 (edition 05/2011) and

Qualicoat EN ISO 11341 / ISO 2810 (edition 02/2010)

**Amount of samples:** For the approval of new tools and replacement tools (if geometry changed)

we need 4 samples x 1,5 m mill finished and 4 samples x 1,5 m powder coated.

Comments: thickness of coating

powder coated	60-80 μm
natural anodized	15-20 μm

Further requirements: profiles should be marked according to profine Norm pN 103, if possible

V. Könnel / CRD-PD Version: 01 29.10.2012